



17025 SO. MAIN ST. GARDENA, CA 90248 | 800.572.9029
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstoneprecast.com

MATERIAL PRODUCT DATA SHEET

Product Name

Classic Pool Coping

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete since 1963. Classic Pool Coping provides distinctive good looks with high strength hardrock concrete. The Classic Pool Coping has a 2" bullnose edge with a ¼" top and bottom reveal. They work well as a design element to refine pool & spa projects. The system includes straights, inside corners, outside corners and radius components. Classic Pool Coping is designed to be used for both commercial and residential applications.

Composition & Materials

Classic Pool Copings are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

Sizes

Pool Coping straights are 14"x24"x2½"; corners are 14"x16"x2½"; radius components vary.

Finishes

Classic Pool Coping available in finishes include: fine grain stipple, and light, medium or heavy sandblast

Colors

Classic Pool Copings are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

Physical / Chemical Properties

Classic Pool Coping is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

February 2025