



17025 SO. MAIN ST. GARDENA, CA 90248 | 800.572.9029  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstoneprecast.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Classic Wall Cap

### Manufacturer

Stepstone, LLC  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-327-7474  
Fax 310-217-1424  
Toll Free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete since 1963. Classic Wall Caps provide distinctive good looks with high strength hardrock concrete. The Classic Wall Cap has a 2" bullnose edge with a ¼" top and bottom reveal. They work well as garden bench seats or as a design element to refine wall appearance. The system includes straights, corners, ends, radius pieces and pilaster caps. Classic Wall Caps are designed to be used for both commercial and residential applications.

### Composition & Materials

Classic Wall Caps are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

### Sizes

Classic Wall Caps are available in standard sizes; Section Widths: Straights, Ends, Corners 8", 10-1/4", 12", 14", 16", 24"; straight lengths are 24"; corner and radius lengths vary. Classic Wall Caps have a thickness of 2 ½".

### Finishes

Classic Wall Cap finishes include: standard smooth finish, light, medium, or heavy sandblast

### Colors

Classic Wall Caps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

### Physical / Chemical Properties

Classic Wall Cap weight is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, LLC for further information*

July 2024